

IRMAGNET ELECTRONIC CO., LTD

Quality Report

Customer	Mr. Abolfazl			Size		F50x40x20	
PO No.				Material		N42. NbFeB	
Inspection Date	1/14/2017			Coating		Ni	
Sampling Qty	10PCS			Principal Components Analysis	(Nb) :33%	(Fe) :64%	
Specialrequest					(B) :1%	Others: 2%	
DIAGRAM							
DIMENSION Tolerance (mm)	Length ± 0.1	Width ± 0.1	Thick ± 0.05	Surfaces Gauss		Φ Magnetic Flux 114820	
	50	40	20	N. pole	S. pole		
	1	50.04	40.02	20.01	3926		3811
	2	50.02	40.01	20.02	3921		3862
	3	50.03	40.03	20.01	3908		3811
	4	50.01	40.03	20.01	3912		3810
	5	50.05	40.02	20.02	3907		3806
	6	50.05	40.02	20.03	3899		3788
	7	50.05	40.01	20.03	3932		3800
	8	50.04	40.02	20.04	3911		3810

9	50.02	40.04	20.02	3902	3899	
10	50.03	40.01	20.02	3929	3824	
Remarks	OK		OK	OK	OK	OK
Passed ☒ Failure ☐						
Inspection Standard: 《QC inspection instruction》						
Client restore: _____ Checked by : _____ Inspected by : _____						